

Beständigkeitsliste Macromelt® Moulding Produkte

Low Pressure Adhesive Injection Moulding

Klebstoff Testmaterial	Standard	Macromelt® OM 652/657	Macromelt® OM 633/638	Macromelt® OM 673/678	Macromelt® OM 710	Macroform® OM 433
Motoröl, Syntetic Mobil 1 OW-40	24 Stunden, RT	+++++	+++++	+++++	+++++	+++++
	28 Tage, RT	+++	+++	+++	+++++	+++++
	24 Stunden, 80 °C	+++	+++	+++	+++++	+
	28 Tage, 80 °C	+	+	+	+++++	-
Motoröl 15W40, Texaco Havoline Formula 3	24 Stunden, RT	+++++	+++++	+++++	+++++	+++++
	28 Tage, RT	+++	+++	+++	+++++	+++++
	24 Stunden, 80 °C	+++	+++	+++	+++++	+
	28 Tage, 80 °C	+	+	+	+++	-
Getriebeöl ATF, Ravenol	24 Stunden, RT	+++	+++	+++	+++++	+++++
	28 Tage, RT	+++	+++	+++	+++++	+++++
	24 Stunden, 80 °C	+	+++	+++	+++++	+
	28 Tage, 80 °C	+	+	+	+++++	-
Getriebeöl 90GL4, Ravenol	24 Stunden, RT	+++++	+++++	+++++	+++++	+++++